M1 Blackout Cloth

Azur Scenic T E V I L O J

Ref: 6320











A 100% blackout material with a particularly fine finish, with M1 flame-retardant rating and available in an impressive range of decorative colours.

With an off-white treatment, this product offers light-reflective and heat-reflective properties.

In addition, this material is also **washable and UV-resistant**, and can be used both indoors and outdoors.


This textile is also great for making **blackout curtains**, as well as for **dressing stage flats**.







Name	M1 Blackout Cloth		
Reference	6320		
Length of whole roll	50 m (in 2 x 25 m)		
Width	280 cm		
Cut-to-length	Yes, minimum 5 linear metres		
Weight	280 g/m²		
Thickness	0.37 mm		
Composition	100% Polyester with white acrylic flocking on reverse		
Flame-retardant rating	() M1		
Acoustic absorption	NRC coefficient 0.38		



Edition July 2023 2/3

Appearance	Fabric with a fine, stylish finish 1 coloured woven side with a smooth and slightly shiny appearance 1 off-white coated side with a lightly quilted appearance			
Supplied in	Rolled full-width			
Care	30° & @ P 🖾			
Storage recommendations	Rolled storage to avoid crease marks.			
Directions for use	Can be made up to any dimensions and with all finishing options (eyelets or rivets, tabs, sleeves, etc.) in our workshops Can be tensioned by stapling Indoor and/or outdoor use			
Recommended use	Dressing wooden structures and frames by stapling Decorative blackout curtains (hotels, reception rooms, lounges, etc.) Roman blinds Roller blinds Japanese screens Linings			
Accessories	Production accessories (straps, ballast chain, etc.) Mounting accessories (clamps, knots, carabiners, etc.)			
Optical index: Light reflection Light absorption Light transmission	73% 27% 0%		DIN EN 410 2011	
Thermal index: Sunlight reflection Sunlight absorption Sunlight transmission UV Transmission	64% 36% o% o%		DIN EN 410 2011	
Gt / Fc	Gt 37%	Fc 52%	DIN EN 13363 DIN EN 14501	
Light fastness	5/8		ISO 105 B02	
Dimensional stability	Warp: 0%	Weft: 0%	ISO 5077	
Tensile strength at break	Warp: 42 daN	Weft: 64 daN	ISO 13934-1	
Elongation at break	Warp: 38 mm	Weft: 27 mm	ISO 13934-1	

CONTACT OUR EXPORT TEAM

+33 (0)6 23 21 50 28



export@azur-scenic.com

The information in this document provides generic values that describe only the standard technical specifications and chemical composition of the products concerned. No guarantee is offered. Any images are non-contractual. The names of the colours are given for information purposes only and do not guarantee a specific colour.